

--ABSTRACT OF THE DISCLOSURE

This invention relates to a process for further processing of small glass particles, for example in the form of scrap glass granulate with a grain size in the range between 0.3 and 4 mm or glass beads with diameters in the range between 0.1 and 2.3 mm.

To be able to produce these glass particles with relatively low energy cost, within the framework of this invention it is provided that the surfaces of the glass particles are brought into contact with a low melting silicate flux or enamel, for example of lead borosilicate, sodium borosilicate, fluoroborosilicate or mixtures thereof in amounts of 2 to 9% by weight, preferably 3 to 5% by weight, and that as a result the glass particles are exposed to heat treatment in the range between 540°C and 800°C, preferably in the range between 560°C and 660°C, at which the low melting silicate flux or enamel melts on the surfaces of the glass particles.

15  
20  
25  
30  
35  
40  
45  
50  
55  
60  
65  
70  
75  
80  
85  
90  
95  
100  
105  
110  
115  
120  
125  
130  
135  
140  
145  
150  
155  
160  
165  
170  
175  
180  
185  
190  
195  
200  
205  
210  
215  
220  
225  
230  
235  
240  
245  
250  
255  
260  
265  
270  
275  
280  
285  
290  
295  
300  
305  
310  
315  
320  
325  
330  
335  
340  
345  
350  
355  
360  
365  
370  
375  
380  
385  
390  
395  
400  
405  
410  
415  
420  
425  
430  
435  
440  
445  
450  
455  
460  
465  
470  
475  
480  
485  
490  
495  
500  
505  
510  
515  
520  
525  
530  
535  
540  
545  
550  
555  
560  
565  
570  
575  
580  
585  
590  
595  
600  
605  
610  
615  
620  
625  
630  
635  
640  
645  
650  
655  
660  
665  
670  
675  
680  
685  
690  
695  
700  
705  
710  
715  
720  
725  
730  
735  
740  
745  
750  
755  
760  
765  
770  
775  
780  
785  
790  
795  
800  
805  
810  
815  
820  
825  
830  
835  
840  
845  
850  
855  
860  
865  
870  
875  
880  
885  
890  
895  
900  
905  
910  
915  
920  
925  
930  
935  
940  
945  
950  
955  
960  
965  
970  
975  
980  
985  
990  
995